



573-364-2338



mo-sci@mo-sci.com



MO SCI, LLC

Appearance

45S5 bioactive glass is white in color and is in powder form.

Chemical Composition (by weight)

Silica (SiO ₂)	43 - 47 %
Calcium oxide (CaO)	22.5 - 26.5 %
Phosphorous pentoxide (P ₂ O ₅)	5 - 7 %
Sodium oxide (Na ₂ O)	22.5 - 26.5 %

Heavy Metals (by ICP) (ASTM F1538 Spec)

As	< 3 ppm
Cd	< 5 ppm
Hg	< 5 ppm
Pb	< 30 ppm
Total (as lead)	< 50 ppm

Physical Properties

Specific Gravity	2.7 (g/cm ³)
Softening Temperature (T _s)	550 ± 10 °C
Melting Temperature	1300 ± 10 °C
Coefficient of Thermal Expansion	16 ± 1 x 10 ⁻⁶ /°C (30 - 300 °C)
Index of Refraction	1.6 (n _D)

Applications

Typical applications of GL0160 include bone grafting biomaterials, repair of periodontal defects, cranial and maxillofacial repair, wound care, blood loss control, stimulation of vascular regeneration, and nerve repair.

Technical information, recommendations, and other statements contained in this document or provided by MO SCI personnel are based on tests or experience that MO SCI believes are reliable, but the accuracy or completeness of such information is not guaranteed. Such information is intended for persons with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information.