



573-364-2338



mo-sci@mo-sci.com



MO SCI, LLC

Appearance

Clear spheres, fibers, powder, or bulk glass which exhibit green fluorescence.

Chemical Composition

- Silica (SiO₂)
- Aluminum oxide (Al₂O₃)
- Calcium oxide (CaO)
- Magnesium oxide (MgO)
- Sodium oxide (Na₂O)
- Iron oxide (Fe₂O₃)
- Rare earth oxide

Physical Properties

Specific Gravity	2.58 (g/cm ³)
Excitation	254 - 365 nm
Emission	Green
Softening Temperature (T _d)	584 ± 10 °C
Glass Transition Temperature	525 ± 10 °C
Coefficient of Thermal Expansion	92 ± 10 x 10 ⁻⁷ /°C (30 - 300 °C)
Compression Strength	29 kg/mm ² (41,200 psi)
Vickers Hardness	550 kg/mm ² (782,000 psi)
Mohs Hardness	6 - 7

Applications

Typical applications of GL1773 include medical imaging, biomedical diagnostics and research, testing media, tracing and art glass enamels.

Technical information, recommendations, and other statements contained in this document or provided by MO SCI personnel are based on tests or experience that MO SCI believes are reliable, but the accuracy or completeness of such information is not guaranteed. Such information is intended for persons with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information.