



Physical Properties

Specific Gravity	4.84 ± 0.1 (g/cm ³)
Softening Temperature (T _d)	527 ± 15 °C
Coefficient of Thermal Expansion (annealed glass)	6.4 ± 1.0 x 10 ⁻⁶ /°C (25-300 °C)
PSD d50	16.5 ± 1.5 μm

Notes

Equivalent to Viox V3242.

MO SCI, LLC ☒ mo-sci@mo-sci.com ☐ 573-364-2338

Technical information, recommendations, and other statements contained in this document or provided by MO SCI personnel are based on tests or experience that MO SCI believes are reliable, but the accuracy or completeness of such information is not guaranteed. Such information is intended for persons with knowledge and technical skills sufficient to assess and apply their own informed judgment to the information.